



BONDKOTE™

MASTIC & FILLER EPOXY COATING SYSTEM

BONDKOTE®—ALL-PURPOSE FILLER, GROUT & BOND AGENT

**FULLY CURED
24-48 HOURS**
(AT A TEMPERATURE OF 70°F)

100%
MAXIMUM BOND
STRENGTH
SELF LEVELING

ULTRA LOW VOCs
AND NO FOUL ODORS
ANTIBACTERIAL / ANTIMICROBIAL

**CURES IN DAMP
ENVIRONMENTS**

1 UNIT (3 GALLONS)
OF PARTS A/B MIXED
COVERAGE WILL VARY PER PROJECT

**TRUSTED BY AMERICA'S
LARGEST CORPORATIONS**

**LOW ENVIRONMENTAL
IMPACT**



SAFERESIN™
A REVOLUTION IN
COATING TECHNOLOGY.

**WELCOME TO THE NEXT
LEVEL OF COATING INNOVATION.**

When we set out to advance epoxy resin technology, we knew we had to start at the foundation. So we looked at the chemistry behind the material and discovered ways in which it could be improved. The result—SafeResin™. Safer, Stronger, Faster, and Easier. The resin technology that is anything but ordinary.

ALL OUR COATINGS ARE SUPER CHARGED BY SAFERESIN TECHNOLOGY.



MIX RATIO 2:1

**CONTRIBUTES TOWARD
VITAL LEED PROJECT POINTS**

LEED BD+C / Low Emitting Materials: 3 Points

LEED ID+C / Low Emitting Materials: 3 Points

(supporting documentation available upon request)

Learn more about Leed Certification at: leed.usgbc.org

RECOMMENDED SUBSTRATES

**Concrete, Stone, Masonry,
Steel, Stainless Steel**

BondKote is a 100% solids, extremely low VOCs, fast curing, technologically advanced epoxy mastic and filler developed with SafeResin technology.

This mastic product has been specifically formulated to meet the requirements as a high performance filler and bonding agent. BondKote provides excellent adhesion and fills in project holes and divots providing a smooth surface to coat over.

USES

- Filler for holes and divots
- And mastic for placing tiles brick & other similar items

BENEFITS

- Excellent bond strength / adhesion
- Excellent abrasion resistance
- Impenetrable to wide range of chemicals and solvents
- Thick-film, single application
- Fast Curing (put into service in 10 -12 hours)
- High temperature stability
- Low/no VOCs
- Completely solid cured product (no microscopic pin holes)

TECHNICAL DATA

Weight (lbs/gal).....	7.67
Volume Solids.....	100%
Color(s).....	Gray, Tan, White, Blue
Flash Point.....	> 200° F (93°C) (ASTM D3941)
Hardness (Shore D min.).....	75 – 80 (ASTM D2240)
Pot Life (@ 70° F).....	25 min
Pot Life (@ 100° F).....	15 min
VOC (mixed lbs/gal).....	0.35*
VOC (mixed g/l).....	42.4*
Recommended Thickness.....	will vary depending on project and application

Temperature Resistance

Non-Immersion dry heat 300° F (149° C) (ASTM D2485)

** If working in a well ventilated area the VOC emissions are effectively zero based on an 8 hour metered OSHA air quality test that produced a 0 PEL reading.*

COVERAGE

will vary depending on project and application

When ordering product, make allowances for any loss of material due to overspray, surface irregularities, etc. (approx. 15 – 20%)

RECOMMENDED SYSTEMS

CONCRETE

1 Unit BondKote Epoxy Mastic/Filler coverage will vary depending on project

MARSITE/GUNITE

1 Unit BondKote Epoxy Mastic/Filler coverage will vary depending on project

FIBERGLASS

1 Unit BondKote Epoxy Mastic/Filler coverage will vary depending on project

STEEL

1 Unit BondKote Epoxy Mastic/Filler coverage will vary depending on project

ORDERING INFORMATION

PACKAGING

Part A Resin 2 gallons (7.56L) contained in 5 gal pail

Part B Hardener 1 gallon (3.78L) contained in 2 gal pail

Mixed: 7.67 lb/gal : 2.03 lb/L

SURFACE PREP INSTRUCTIONS

All surfaces must be cleaned and dry, free of dust, dirt, oil or other foreign matter. Concrete should be etched with KoreKote Concrete Cleaner. Primer may be required for some concrete surfaces depending on the surface grade quality.

MIXING INSTRUCTIONS

Mix **2:1 ratio** by volume of **Part A (resin)** and **Part B (hardener)** together. Mix thoroughly until uniform color and consistency throughout. Mechanical mixing (drill with mixing paddle) is critical.

Mechanically pre-mix both Part A and Part B components individually for approx. 1 minute. Then mix combined compound with mechanical mixer at 400-600 rpm for 3 to 4 minutes. Mechanical mixing blades are recommended.

APPLICATION

Mix batches of the material that are appropriate for the grout or filler project you are working on so that all mixed material can be placed and finished within 30 minutes. Use a trowel or putty knife to scoop material and place/spread in desired project area. When material is spread out in a thinner layer, the worklife is extended to approximately 35 minutes (do not apply in temperatures below 50°F). For detailed handling and safety instructions, please refer to the product **SDS Documents**.
Downloaded SDS at: www.korekote.com/download

APPLICATION TEMPERATURE

The curing profile of KoreKote® coating products will vary depending upon the ambient conditions of your project, including temperature and humidity. To achieve the best cure result follow the recommended cure cycle time and conditions on the TDS that came with your order. Always run a test before full application is initiated. Also, substrate temperatures can have a significant impact on curing profile – make sure your substrate is within recommend temperature ranges before applying a KoreKote® coating product.

POT LIFE

Pot life of mixed coating is approximately 20 minutes at 70°F if material is left as a unit in mixing container. Higher temperatures reduce pot life and accelerate curing. **CAUTION:** Mixing large quantities (more than a 3 gallon batch size) generates significant heat and shortens pot life.

Do not leave large quantities of mixed material in its container beyond its pot life, as significant heat will be generated and can melt container or cause a safety hazard.

CLEANUP

Use denatured alcohol (not necessary to use harmful/toxic solvents) to cleanup uncured material and tools. For small amounts of excess product, mix Part A and Part B according mixing instructions. Allow material to solidify prior to disposal. **DO NOT** use solvents to clean epoxy from skin. Consult MSDS and TDS for complete handling and safety information.

STORAGE

The minimum shelf life of 24 months can be achieved provided the material remains stored in closed containers, in a dry environment, out of direct sunlight and at stable temperatures between 50° to 100°F. If product is exposed to temperatures below 50° F crystallization of the material may occur. Crystallization can be reversed with no adverse affects to the material if it is placed in elevated temperatures of 120° to 150° F for a short period of time. Ensure product has returned to its original pre crystallization state prior to application.

APPLICATION EQUIPMENT

BondKote can be applied using several different tools depending on the specific application or project requirements. For projects with larger surface areas a trowel tool is recommended but for smaller projects that require filling of holes/divots, etc. a putty tool usually provides the best solution.

RECOMMEND CLEANING AGENT

Denatured Alcohol

GROUT TOOL

PUTTY TOOL

ROLLER

Specs: 3/8" woven nap with solvent resistant core (designed specifically for epoxy application)

Cleaning Agent: Denatured Alcohol

PERFORMANCE

Service temperature	-67° – 600°F (depending on the application)
Impact resistant	Yes
Water seal	Yes
Solvent and chemical spill resistant	Yes
Oil and gas spill resistant	Yes

LIQUID PROPERTIES

Form	Semi-thick liquid
Non-drip	Yes
Low/no VOCs	Yes
Viscosity	at 77°F (25°C) Part A 50,000 cP / Part B 300 cP / Mixed 45,000 cP
Pot life	15 minutes
Gel time	30 minutes
Full cure time	4 – 8 hours (depending on temperature and application)
Shelf life	24 months
Cure method	Chemical reaction
Application temperature	50° – 80°F

CURED PROPERTIES

Permeable	No
Can be painted/stained	No
Fills gaps	Yes
Removable	No
Flexible	Yes
Flash Point	> 200°F (93°C) (ASTM D3941)

MIXING & HANDLING

Number of components	2
Mix ratio	2:1
Application methods	Trowel tool, grout tool, putty tool, roller etc.

MINIMUM DRY TIME

70° F and 50% relative humidity. (ASTM D1640)

To Touch: 2 hours

To Handle: 4 hours

To Recoat: 2.5 – 4 hours

CURE SCHEDULE

Shore D 75 – 80 (ASTM D2240) @ 70° F and 50% relative humidity. For Immersion Service: 11 hours.

Shore D 75 – 80 @ 100° F and 50% relative humidity.

For Immersion Service: 9 hours.

POST CURING

It is not necessary for most applications, however BondKote may be post cured to expedite curing and increase chemical resistance for extremely aggressive environments. Post cure for minimum of 2 hours at 250° F or 6 – 8 hours at 150° F for maximum resistance.

APPLICATION TEMPERATURE

Apply at 5° F (3° C) above dew point. The following chart provides the preferred conditions for temperature and humidity. The conditions provided in the chart along with good circulation are important to maintain throughout the cure cycle.

	Coating	Substrate	Ambient	Humidity
Preferred	95 – 105° F	50 – 120° F	70 – 100° F	0 – 90%
Minimum	90° F	50° F	50° F	0%

DISCLAIMER

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local laws and local regulations remains the responsibility of the user.

+ SUGGESTED FIRST AID

IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. Call a POISON CONTROL CENTER if you feel unwell.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists: Get medical advice. Immediately call a doctor.

IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin with water or shower. Wash contaminated clothing before reuse. If skin irritation or rash occurs: Get medical attention.

IF INHALED: Remove person to fresh air and keep comfortable for breathing. Immediately call a doctor.

For detailed handling and safety instructions, please refer to the product SDS Documents. Downloaded SDS at: www.korekote.com/download

!!! WARNING



May cause an allergic skin reaction. Causes skin and serious eye irritation. Specific treatment (see FIRST AID section on this label). Avoid breathing vapors. Contaminated work clothing must not be allowed out of the workplace. Wear protective gloves and eye protection. Wash hands and exposed skin thoroughly after handling. Dispose of container in accordance with local regulations. **For detailed handling and safety instructions, please refer to the product SDS Documents. Downloaded SDS at: www.korekote.com/download**

!! KEEP OUT OF REACH OF CHILDREN !!

CONTAINS: Reaction products of Epichlorohydrin and Bisphenol, Alkyl Glycidyl Ether.

DISCLAIMER

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local laws and local regulations remains the responsibility of the user.

WARRANTY

KoreKote, Inc. warrants its products to be free of manufacturing defects in accord with applicable KoreKote quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by KoreKote.

NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY KOREKOTE, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.